



The clear choice.

Safety and Security Window Films

Solar Performance Characteristics

Film	Total Solar Heat Rejected	Solar Glare Reduction	Visible Light Transmission	Solar Energy Reflected	Solar Energy Absorbed	Shading Coefficient
Lustalux Clear 4mil	21%	13%	87%	8%	19%	.91
Lustalux Clear 7mil	22%	13%	87%	8%	19%	.90
Lustalux Clear 8mil	24%	17%	83%	10%	21%	.74
Lustalux Clear 10mil	23%	14%	86%	8%	21%	.76
Lustalux S20 Silver 4mil	78%	85%	15%	45%	45%	.25
Lustalux S20 Silver 8mil	78%	86%	14%	44%	47%	.25
Lustalux SB20 Bronze 4mil	78%	82%	18%	42%	49%	.25
Lustalux SS20 S.Steel 20 4mil	63%	78%	22%	20%	61%	.42
Lustalux SS20 S.Steel 35 4mil	48%	59%	41%	14%	47%	.60
Lustalux SS20 S.Steel 20 8mil	64%	79%	21%	20%	62%	.41

All performance results are based on internal application to 6mm single pane clear glass.
 All data reported has been tested using ASHRAE, ASTM, IWFA and AIMCAL. Performance results are subject to variations within industry standards and are only intended for estimating purposes.