

lustalux.

7 Mil (175 Micron) Silver Combination Film

Colour Silver

SOLAR SPECIFICATIONS

Solar heat rejected >60%

Solar glare reduction >80%

Visible light transmitted (at 550nm) 16%

Solar energy reflected 51%

Solar energy absorbed 36%

Shading coefficient 0.26

Mirror index 3.6